

Quik-Therm Multi Purpose Insulation (MPI) is a high performance continuous rigid insulation product consisting of superior closed cell, lightweight and resilient expanded polystyrene (EPS) layered on two sides with advanced reflective polymer facers. Quik-Therm MPI is a multi-functional, durable and flexible insulation which can be used in a wide variety of building insulation applications. MPI is an all in one air, vapour, radiant and radon barrier and is available in rolls and sheets. Quik-Therm MPI has been tested by Canadian certified laboratories and the test results are supported by leading building scientists.



- In one product, Quik-Therm MPI meets air, vapour and radiant barrier requirements
- Excellent dimensional stability flexible and durable
- Depending on thickness, Quik-Therm MPI can be bent to 90 degree angles. Does not easily crack, chip or break
- NO thermal drift, and its R-value will remain stable over its entire service life
- Quik-Therm MPI does not promote mildew and mold
- Contains no dyes, formaldehyde, or ozone depleting blowing agents
- Recyclable Quik-Therm MPI may contain up to 15% recycled content
- Manufactured in thicknesses from 1/2" to 6". Variable densities.
  4' X 8' sheets and 4' X 72' X 1/2" thick rolls (288 ft²).



## **MPI Testing & Technical Data**

## **Morrison Hershfield**

"The use of effective R-values when evaluating the thermal resistance of an assembly is preferable to using the nominal R-value of the insulation alone. The benefits of this approach have been demonstrated in results obtained through laboratory tests such as ASTM C1363 and by data published in ASHRAE 90.1. Quik-Therm Insulation Solutions Inc. has undertaken a program of full scale thermal performance testing to ASTM C1363-05 Standard Test Method for Thermal Performance of Building Materials and Envelope Assemblies by Means of a Hot Box Apparatus."

- Mark Lawton - Senior Building Scientist

## **Quik-Therm Effective Thermal Resistance**

Quik-Therm Thickness	2x4 Wood Frame with R-12 Batt	2x6 Wood Frame with R-20 Batt	Wood Frame Empty Cavity	2x6 Steel Frame with R-20 Batt	Interior Masonry	Exterior Masonry
1.5"	21	26	11	17	11	8
2"	23	28	13	19	13	10
3"	28	32	17	23	18	15
4"	32	36	21	27	22	19
5"	36	40	25	31	26	23
6"	40	44	29	35	30	27

Nominal R-Value Testing ASTM C-518 = R-4.18 | Steel Framing ASHRAE Table A3.13

## **ASTM C1363 Test Results**

Description of Test Samples Starting from Exterior	Overall Thermal Resistance (hr·ft²·F/Btu), R-value (R <sub>u</sub> )
Cement board cladding, 2" Quik-Therm MPI, 7/16" OSB, 2x4 wood studs, empty cavity, 1/2" drywall	13.2
3" Quik-Therm MPI, 3/8" drainage gap, 7/16" OSB, 2x4 wood studs, empty cavity, 3/8" drywall	17
3.5" Quik-Therm, 7/16" OSB, 2x4 wood studs, empty cavity, 1/2" drywall	19.5
Concrete Wall, 6" Quik-Therm, steel framing, empty cavity, 1/2" drywall	29.9
2" Quik-Therm, 7/16" OSB, 2x4 wood studs, R-13 fiberglass batts, 3/8" drywall	23.1
2" Quik-Therm, 7/16" OSB, 2x6 wood studs, R-20 fiberglass batts, 1/2" drywall	28.3
Wood cladding, 3/8" rain screen, 3" Quik-Therm, 2x4 wood studs, R-12 fiberglass batts, 1/2" drywall	29.96













(888) 735-3012

Property	Nominal Value			Test Method
Dimensional Stability Maximum Linear Change, %	1.5			ASTM D2126
Length Tolerance, mm (in)	±3.2 (±0.125)			_
Width Tolerance, mm (in)	±1.6 (±.063)		_	
	Type 1	Type 2	Type 3	
Nominal R-Value	3.81	4.18	4.40	ASTM C518
Nominal Density, pcf (kg/m³)	1.0 (16)	1.4 (23)	1.8 (29)	ASTM D1622
Compressive Strength, psi (kPa)	12.6 (87)	19.7 (136)	30 (207)	ASTM 1621-04
Water Vapour Transmission, perms	<1.0			ASTM E96
Air Permeance (L/s·m²)	0.0139			ASTM E2178-13
Effective R-Value Testing See Table		e Table Above	9	ASTM C1363
Limiting Oxygen Index	26 %			ASTM D2863-97
Flame Spread	250			CAN/ULC - S102.2
Smoke Developed	410		CAN/ULC - S102.2	

Quik-Therm Insulation Solutions Inc. (204) 736-3012

6" Quik-Therm and fiber cement board siding meets the requirements of CAN/ ULC-S101 as required by Article 3.2.3.8. Test Report: T1035-4 QAI Laboratories.